



Castrol Alphasyn HTX Range

High Temperature Synthetic Gear Lubricant

Description

The Alphasyn™ HTX gear oil range of synthetic lubricants are based on polyalpha-olefin (PAO) fluids and sulphur/phosphorus antiwear additive technology providing outstanding thermal stability and good load carrying capacity.

Application

The Alphasyn HTX range has been formulated for use in most types of light to medium duty enclosed gear systems but should not be used for heavy / shock loaded systems. Alphasyn HTX is also suitable for bearings and circulatory systems operating at high temperatures.

The outstanding oxidation and thermal stability of Alphasyn HTX allows oil change intervals to be extended in circumstances where extreme temperatures would result in a short service life if using conventional mineral oil based lubricants. This allows demonstrable savings to be made by reducing the level of maintenance required.

All products in the Alphasyn HTX range have very low pour points and excellent viscosity/temperature characteristics, allowing their use in low temperature as well as high temperature applications.

The Alphasyn HTX range is fully compatible with nitrile, silicone and fluopolymer seal materials.

Alphasyn HTX is classified as follows:
DIN Classification is CLP

Alphasyn HTX grades meet the requirements of:
DIN 51517 Part 3
David Brown Type A
AGMA EP4

Advantages

- Good thermal and oxidative stability provides reliable operation and extended operating life when compared to mineral oil based products.
- Inherently high viscosity index makes the product suitable for operations operating over a wide temperature range.
- Good antiwear and load carrying abilities including FZG > 12 rating under A16.6/110 test conditions eliminates wear and prolongs gear tooth life.
- Good water separation and demulsification characteristics means reduced down time through prolonged lubricant life and increased equipment reliability.
- PAO based lubricant provides good compatibility with seals, paints and mineral oil based lubricants.

Typical Characteristics

Name	Method	Units	HTX 68	HTX 150	HTX 220	HTX 320	HTX 460	HTX 1000
Density at 15°C	ISO 12185, ASTM D4052	g/ml	0.86	0.87	0.87	0.87	0.87	0.88
K.V at 40°C	ISO 3104, ASTM D445	mm ² /s	68	150	220	320	460	1000
K.V at 100°C	ISO 3104, ASTM D445	mm ² /s	10.8	20	27	37	47	85
Viscosity Index	ISO 2909, ASTM D2270	-	150	150	155	160	160	165
Pour Point	ISO 3016, ASTM D97	°C	-39	-39	-39	-36	-36	-36
Flash Point, PMC	ISO 2719, ASTM D93	°C	220	220	220	230	230	230
Foam Sequence I	ISO 6247, ASTM D892	mls/ mls	0/0	0/0	0/0	0/0	0/0	0/0
FZG (A6.6/110) Fail Stage	ISO 14635-1, ASTM D51354	-	-	-	>12	>12	>12	>12
Rust Test (24hrs Distilled Water)	ISO 7210, ASTM D665B	-	Pass	Pass	Pass	Pass	Pass	Pass

Subject to usual manufacturing tolerances.

Castrol Alphasyn HTX Range

29 Jan 2018

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Industrial, Technology Centre , Whitchurch Hill , Pangbourne , Reading , RG8 7QR , United Kingdom

<http://msdspds.castrol.com>